

Low Cost Electrasil™ -3

Product Description:

Electrasil™-3 is a silicone based conductive adhesive that provides a low cost technique to create a thermally and electrically conductive bond between Printed Circuit Boards (PCBs) and metal carriers or heat sinks. This is a much lower cost alternative to our earlier relatively expensive silver based bonding compounds. Although the formulation of this material was specifically targeted toward meeting the critical requirements and performance goals for power amplifier and other electronics cooling applications, it also lends itself extremely well to specialized PCBs need to be mounted to a metal surface or housing. A variety of graphitic carbon composition and structures are available to suit individual customer needs. As a thin sheet of thermoplastic elastomer material, it provides a highly conductive strong bonding between the adjacent surfaces. Being an elastomer, it accommodates any TCE mismatch of the bonded layers, so there is no residual stress left in the bonded assembly. It can withstand a continuous operating temperature of 260°C (500°F) as well as multiple excursions up to 288 °C (550 °F) for subsequent operations, such as solder reflow for component installation. The ability to retain its bond strength and thermal and electrical performance after multiple high temperature excursions at these higher temperatures also lends itself very well to the use of higher temperature lead-free solders. As a silicone elastomer, its flexible nature makes it ideally suited for improved life cycle performance, when used with thermoplastic circuit materials such as PTFE where large X and Y dimensional tolerances are tight.

Physical Characteristics:

The adhesive is a silicone based thermoplastic elastomer that utilizes both mechanical and chemical bonding mechanisms to insure reliable adhesion at the bond-line interface. The high thermal and electrical conductivity is due to proprietary fillers that ensures very low electrical and thermal resistivity. With the proven stability under adverse environmental conditions of the silicone adhesive (in space, land or water), combined with excellent physical and electrical properties of the conductive fillers, Electrasil™-3 bonded PCBs would consistently deliver high performance over an extended life cycle. It has excellent bond strength and thermal shock performance.

Applications:

Electrasil™-3 is used to bond PCBs to metal carriers (heat sink) prior to the assembly of components. If the customer prefers, American Standard Circuits offers the bonding service to adhere the PCB to the metal carrier. The bonding process requires a minimum pressure of 50 PSI to be applied to the bonding surface and a heat source capable of maintaining a bond line temperature of 165 °C (330 °F) for 30 minutes. Pressure is applied through use of a Fixture Clamping Device, Heated Press or an Autoclave. Heat sources include hot plate, I/R Oven, Convection Oven or an Autoclave. American Standard Circuits has application engineers on staff to help design a compatible bonding process for our customers.

Property	Value	Method of Test
Shelf Life	6 months when stored between 50 and 70 F	
Thickness, mils	3 to 200	
Specific Gravity	2.0 to 3.0 ± 0.1	ASTM D297
Durometer, Shore A	68 to 77	ASTM D2240
Tensile (PSI)	180 Min	ASTM D412
Elongation (%)	100 Min	ASTM D412
Tear Strength (PPI)	40	ASTM D624
Bond Strength, PPI ⁽¹⁾	20	ASTM D429
Continuous Operating Temp	-60 C to +260 Deg C	
Thermal Conductivity, W/mK	5-8	ASTM C408
Flame Retardance	Pass	UL94VO
Volume Resistivity, at 77 F, Ohm-cm ⁽²⁾	0.007 Max	ASTM D991 (modified) or Mil-G-83528

(1). All Electrasil™-3 samples maintained a cohesive bond after a convection reflow process (at 230 °C) and accelerated life testing (85 °C / 85 % RH for 1000 hours) as demonstrated by destructive peel tests. (2). Resistivity value is also dependent on the type of metal carrier finish used.



The information in this data sheet is intended to assist you in designing with ASC Thermal Management Materials. It is not intended to and does not create any warranties express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on this data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of ASC Thermal Management Materials for each application.